

Superconducting zero temperature phase transition in two dimensions and in the magnetic field

Wen-Chin Wu* and Igor F. Herbut

Department of Physics, Simon Fraser University, Burnaby, British Columbia, Canada V5A 1S6

(February 1, 2008)

We derive the Ginzburg-Landau-Wilson theory for the superconducting phase transition in two dimensions and in the magnetic field. Without disorder the theory describes a fluctuation induced first-order quantum phase transition into the Abrikosov lattice. We propose a phenomenological criterion for determining the transition field and discuss the qualitative effects of disorder. Comparison with recent experiments on MoGe films is discussed.

PACS numbers: 74.40.+k, 71.30.+h, 72.15.Rn

I. INTRODUCTION

In the last decade it became well appreciated that the superconducting transition can be tuned not only by changing temperature, but also by varying some other parameter, like the level of disorder, magnetic field, film thickness, or doping of a high- T_c material, at *zero temperature* ($T = 0$) [1]. This is an example of a *quantum* phase transition [2], where the order-disorder transition is not brought about by increasing the entropy of the system, as in the finite temperature case, but by changing the quantum mechanical ground state in a fundamental way. A particularly interesting example is the superconductor-insulator transition in two dimensions (2D) [3], where the superconducting state at $T = 0$ is destroyed by increasing the level of static disorder in the system. For a while it has been thought that the magnetic field would have a similar (but not exactly the same) disordering effect on the superconducting ground state [1,4,5]; recently, however, the experiments of Mason and Kapitulnik [6] have suggested that by increasing the magnetic field at $T = 0$ the 2D system undergoes a superconductor-metal phase transition, and, moreover, that this transition may actually be discontinuous. The metallic state they found seems to be quite unusual, in that its resistivity is anomalously low, and it exhibits a very large magnetoresistance. Only at a higher magnetic field the expected 2D insulating state is recovered [6].

Motivated by these intriguing results, in this paper we study theoretically the $T = 0$ superconducting phase transition in 2D and in the perpendicular magnetic field. We begin by demonstrating that, due to the pair-breaking nature of the magnetic field, in 2D (and without disorder) there exists a regular Ginzburg-Landau-Wilson (GLW) theory for the fluctuating superconducting order parameter even at $T = 0$. Long time ago, it was shown by Maki and Tsuzuki [7] that the GLW theory in the magnetic field and in 3D is almost regular at $T = 0$; the quartic term coefficient was singular only weakly (logarithmically) as T approaches zero. We show that in 2D this singularity is removed by the absence of the third direction along which the motion would be unaffected by the field. The resulting GLW theory describes the quan-

tum fluctuations of the lowest Landau level (LLL) superconducting order parameter (OP), and bears close resemblance to the finite- T GLW theory for a 3D superconductor. Based on the existing understanding of the finite- T Abrikosov transition in 3D, we then argue that the quantum Abrikosov transition in 2D and without disorder is generically first-order, and propose a phenomenological criterion for determining the first-order superconductor-metal transition field H_{sm} . In particular, we show that the true transition field H_{sm} at $T = 0$ is always below the mean-field critical field H_0 , and that the quantum phase transition is from the superconducting into a zero-temperature equivalent of the vortex liquid phase: a metallic phase, strongly renormalized by the superconducting fluctuations, which we propose may be related to the anomalous metal observed by Mason and Kapitulnik.

In a real experiment, of course, disorder is always present, and may actually be quite strong, so it can be expected to play an important role in determining the nature of the transition. In principle, quenched disorder lifts the degeneracy of the LLL for the order parameter, and, we argue, if strong enough could bring back the continuous phase transition to a glassy superconducting phase. We provide a qualitative discussion of this phase transition at strong disorder within the framework of a self-consistent Hartree approach. The superconducting transition in this approach would correspond to the condensation into the lowest extended Hartree eigenstate, that in principle needs to be computed numerically. At weak disorder, on the other hand, based on the existing renormalization group studies of the thermal Abrikosov transition, we expect that the superconducting transition at $T = 0$ remains discontinuous.

The organization of the paper is as follows. In Sec. II, we derive the effective GLW action appropriate for the superconductor-metal quantum phase transition in 2D in the magnetic field and without disorder. In Sec. III, we show how this effective action leads to a fluctuation induced first-order transition, and calculate the critical field. In Sec. IV, we discuss the qualitative effects of quenched disorder on the phase transition, and in Sec. V, we relate our results to experiment and other theoretical studies and provide a brief summary. Technical details

are relegated to the Appendices.

II. QUANTUM ACTION AT $T = 0$

We begin by considering the $T = 0$ action for a system of 2D fermions in a magnetic field ($\hbar = c \equiv 1$)

$$S = \sum_{\sigma} \int d^2\mathbf{r} d\tau \left[\psi_{\sigma}^{\dagger} \partial_{\tau} \psi_{\sigma} + \frac{1}{2m} |(\nabla - ie\mathbf{A})\psi_{\sigma}|^2 - \mu \psi_{\sigma}^{\dagger} \psi_{\sigma} - \frac{V}{2} \psi_{\sigma}^{\dagger} \psi_{-\sigma}^{\dagger} \psi_{-\sigma} \psi_{\sigma} \right], \quad (1)$$

where $\psi \equiv \psi(\mathbf{r}, \tau)$, σ , e , and m denote the spin, charge, and mass of fermions, μ is the chemical potential, and $\mathbf{H} = \nabla \times \mathbf{A}$ is the external magnetic field. The integration over the imaginary time τ is over the whole real axis ($T = 0$), and we neglect the Zeeman coupling of the magnetic field to spin. We assume the interaction $V > 0$ which corresponds to the s -wave attraction. The partition function is the functional integral over Grassman fields ψ with the action S as the Boltzmann weight. Following the standard Hubbard-Stratonovich decoupling procedure [8] in the Cooper channel, the action can be rewritten as

$$S = \int d^2\mathbf{r} d\tau \left[\psi_{\sigma}^{\dagger} \partial_{\tau} \psi_{\sigma} + \frac{1}{2m} |(\nabla - ie\mathbf{A})\psi_{\sigma}|^2 - \mu \psi_{\sigma}^{\dagger} \psi_{\sigma} - |\Delta(\mathbf{r}, \tau)|^2 - \sqrt{V} \Delta(\mathbf{r}, \tau) \psi_{\uparrow}^{\dagger} \psi_{\downarrow}^{\dagger} - \sqrt{V} \Delta^{\dagger}(\mathbf{r}, \tau) \psi_{\downarrow} \psi_{\uparrow} \right] \quad (2)$$

in terms of the fluctuating superconducting order parameter (OP) $\Delta(\mathbf{r}, \tau)$. (The sum over the repeated spin indices is here assumed.) Since the action now became quadratic in the fermionic fields, in principle they could be integrated out so that one is left with the action in terms of the OP only. Furthermore, one could attempt to expand the resulting action in powers of the OP,

$$S = S_2 + S_4 + \dots = \int d\mathbf{1} d\mathbf{2} K_2(\mathbf{1}, \mathbf{2}) \Delta^{\dagger}(\mathbf{1}) \Delta(\mathbf{2}) + \int d\mathbf{1} d\mathbf{2} d\mathbf{3} d\mathbf{4} K_4(\mathbf{1}, \mathbf{2}, \mathbf{3}, \mathbf{4}) \Delta^{\dagger}(\mathbf{1}) \Delta(\mathbf{2}) \Delta^{\dagger}(\mathbf{3}) \Delta(\mathbf{4}) + \dots, \quad (3)$$

where we denoted $\mathbf{1} \equiv (\mathbf{r}_1, \tau_1)$ for brevity. The partition function is the functional integral over all configurations of the *fluctuating* OP. The quadratic and the quartic terms in the action can be represented diagrammatically as in Fig. 1. As well known, without the magnetic field these diagrams would lead to singular expressions for K_2 and K_4 at $T = 0$, as the system would always be unstable towards the formation of Cooper pairs. Finite magnetic field, however, acts as a pair-breaker, and one may expect it to regularize the kernels in the GLW expansion, similarly as disorder does for the d -wave pairing [9]. In the rest of this section we will show how this happens in




FIG. 1. Diagrammatic representation of the quadratic S_2 and the quartic S_4 terms of the action in (3). Solid lines correspond to single-particle Green's functions.

2D, and obtain the GLW theory for the superconducting transition at $T = 0$.

In the magnetic field the momentum is no longer a good quantum number, but the gauge invariance has to be maintained in the theory. This dictates that instead of the standard gradient expansion, the kernels in the GLW action can now be expanded in powers of the covariant derivative $\nabla - ie^*\mathbf{A}$, with $e^* = 2e$. Furthermore, assuming a weak coupling V , the transition into the superconducting state can be expected at a low magnetic field, so to calculate the diagrams in Fig. 1 one may follow Gor'kov and use the “semi-classical” approximation [10,11], for the single-particle Green's function

$$G_{\nu}(\mathbf{r}_1, \mathbf{r}_2) = e^{i\phi(\mathbf{r}_1, \mathbf{r}_2)} G_{\nu}^0(\mathbf{r}_1, \mathbf{r}_2). \quad (4)$$

Here ν is the Matsubara frequency. The phase is determined by $\phi(\mathbf{r}_1, \mathbf{r}_2) = e \int_{\mathbf{r}_2}^{\mathbf{r}_1} \mathbf{A} \cdot d\mathbf{l}$, integrating the gauge field over the straight path from $\mathbf{r}_2$ to $\mathbf{r}_1$, and G^0 is the propagator in the absence of magnetic field. Finally, since the OP feels the magnetic field, one may expand it in terms of the Landau levels, which are the solutions of the single-particle Schrödinger equation in the magnetic field for charge $2e$. Near the superconducting transition only the lowest Landau level (LLL) configurations of the OP need to be retained in the effective action [12], since the higher Landau levels are not critical, and their effect in principle could be only to renormalize the coefficients in the GLW expansion for the LLL modes. Choosing the Landau gauge $\mathbf{A} = H(0, x, 0)$ to represent the magnetic field $\mathbf{H} = H\hat{z}$ perpendicular to the 2D plane, the OP may then be expanded in terms of the LLL functions

$$\Delta(\mathbf{r}, \tau) \equiv \sum_{-\infty}^{\infty} C_n(\tau) e^{ikny} \psi_n(x); \quad \psi_n(x) = e^{-eH(x - \frac{kn}{2eH})^2}, \quad (5)$$

where $k = 2\pi/L$ (L is the linear size of the system) and n is an arbitrary integer.

Going to Matsubara frequency space, the quadratic part of the action can be written as $S_2 = \int d\omega \bar{S}_2(\omega)$, and to the lowest order in small parameter $\omega\tau_H$ we find (see Appendix A)

$$\bar{S}_2(\omega) = [1 - g \ln(2\Omega\tau_H) + \sqrt{\pi} g \tau_H |\omega|] \langle |\Delta_{\omega}(\mathbf{r})|^2 \rangle, \quad (6)$$

where $\tau_H = \ell/v_F$ is the cyclotron time with $\ell = 1/\sqrt{2eH}$ the magnetic length for charge $2e$ and v_F the Fermi velocity. $g = \mathcal{N}V/2$ is the dimensionless coupling ($\mathcal{N} = m/2\pi$ is the constant density in 2D), $\Delta_\omega(\mathbf{r})$ is the Fourier transform of $\Delta(\mathbf{r}, \tau)$, and Ω is the usual ultraviolet cutoff. Also

$$\begin{aligned} \langle |\Delta_\omega(\mathbf{r})|^2 \rangle &= \int d\mathbf{r} |\Delta_\omega(\mathbf{r})|^2 \\ &= \frac{2\pi}{k} \sum_n |C_n(\omega)|^2 \sqrt{\frac{\pi}{2eH}}. \end{aligned} \quad (7)$$

Similarly, the quartic part of the action $S_4 = \int d\omega d\omega_1 d\omega_2 \bar{S}_4(\omega, \omega_1, \omega_2)$, where at zero frequencies [13] (see Appendix B),

$$\bar{S}_4(\omega = \omega_1 = \omega_2 = 0) = a \frac{g^2 \tau_H^2}{\mathcal{N}} \langle |\Delta_0(\mathbf{r})|^4 \rangle \quad (8)$$

with the constant $a = 4\pi[\ln(1 + \sqrt{2})]^2$ and the average

$$\begin{aligned} \langle |\Delta_0(\mathbf{r})|^4 \rangle &= \int d\mathbf{r} |\Delta_{\omega=0}(\mathbf{r})|^4 \\ &= \frac{2\pi}{k} \sum_{n,m,p,q} \delta(n - m + p - q) C_n(0) C_m^*(0) C_p(0) C_q^*(0) \\ &\quad \times \sqrt{\frac{\pi}{4eH}} e^{-\frac{k^2}{4eH}[(n^2+m^2+p^2+q^2)-(n+m+p+q)^2/4]}. \end{aligned} \quad (9)$$

Note that the coefficient before $\langle |\Delta_0(\mathbf{r})|^4 \rangle$ is finite in a finite magnetic field. At zero field it diverges, as well-known. In 3D the same coefficient is $\propto -\ln(T/H)$, and logarithmically divergent as $T \rightarrow 0$ [7]. This is a consequence of the fact that the motion in the z direction remains unaffected by the magnetic field. In 2D, however, the singular behavior of the Landau expansion around the normal state $\Delta = 0$ for the $T = 0$ action is completely cured.

The effective GLW action for the superconductor-metal phase transition in 2D at $T = 0$ can thus be written as

$$S_{\text{GLW}}[\Phi] = \int d\mathbf{r} d\tau [\Phi^\dagger |\partial_\tau| \Phi + \alpha |\Phi|^2 + \beta |\Phi|^4] \quad (10)$$

where $\Phi \equiv \Phi(\mathbf{r}, \tau)$, and the partition function is $Z = \int D[\Phi^*, \Phi] \exp(-S_{\text{GLW}}[\Phi])$. In principle the action contains higher powers of the field and the higher order time derivatives, but we make the usual approximation in retaining only the most relevant terms. The operator $|\partial_\tau|$ corresponds to $|\omega|$ in Matsubara space and we have rescaled the field $\Phi = (\sqrt{\pi} g \tau_H)^{1/2} \Delta$ to bring the coefficient of the $|\omega|$ term in (10) to unity. Thus $\alpha = [g^{-1} - \ln(2\Omega\tau_H)]/(\sqrt{\pi}\tau_H)$ and $\beta = a/(\pi\mathcal{N})$.

III. FLUCTUATION INDUCED FIRST-ORDER TRANSITION

When the fluctuations of the OP are ignored (the mean-field approximation), the system described by the

action (10) at $T = 0$ undergoes a continuous phase transition from normal to the Abrikosov superconducting phase as the magnetic field is decreased, at the point where $\alpha = 0$. The mean-field critical field is thus $H_0 = 2\Omega^2/(ev_F^2)e^{-2/g}$, and exponentially small for a weak coupling g . One can easily verify that this satisfies the standard relation $H_0\xi^2 \approx 1$ where ξ is the superconducting coherence length. This mean-field critical field is simply the end ($T = 0$) point of the standard $H_{c2}(T)$ Abrikosov line in the H - T phase diagram of a 2D type-II superconductor. However, today it is well established both theoretically [14–16] and experimentally [17,18], that at finite T Abrikosov transition is one of those rare cases where fluctuations even *qualitatively* alter the nature of the transition, turning it into a first-order in the clean case. This may be understood as a consequence of the macroscopic degeneracy of the LLL manifold, which is a unique feature of the Abrikosov transition, and which greatly enhances the effect of fluctuations. Any OP configuration within the LLL can be parametrized in terms of its zeroes (vortices), and the Abrikosov transition is equivalent to a freezing transition of a complicated classical many body system, which is then typically first order [16]. Our quantum action at $T = 0$ is almost identical to the finite- T GLW theory for a 3D superconductor in the magnetic field (except for a linear instead of a quadratic derivative with respect to the third coordinate), and one may expect that, in this case, quantum fluctuations of the OP may also turn the $T = 0$ transition into first order. To approximately obtain the critical magnetic field H_{sm} of the first-order transition, it is convenient to work with dimensionless quantities and first rescale the fields, lengths, and time as $(4\pi\ell^2\tau_H\beta)^{1/4}\Phi \rightarrow \Phi$, $r/(\sqrt{\pi}\ell) \rightarrow r$, and $\tau/\tau_H \rightarrow \tau$. The action in (10) then becomes

$$S_{\text{GLW}}[\Phi] = \int d\mathbf{r} d\tau \left[g_\tau \Phi^\dagger |\partial_\tau| \Phi + g_\alpha |\Phi|^2 + \frac{1}{4} |\Phi|^4 \right], \quad (11)$$

where the two dimensionless couplings are $g_{\tau,\alpha} = (1/\tau_H, \alpha)(\pi\ell^2\tau_H/4\beta)^{1/2}$. First, consider only the OP configurations that have no τ dependence ($\omega = 0$ modes). For those the first term of (11) vanishes, and the thermodynamics of the system would depend exclusively on the single dimensionless coupling g_α . The theory would then look zero-dimensional, however, this is deceiving: the macroscopic degeneracy of the LLL still remains. In fact, without the first term the partition function with the action (11) would be identical to the finite- T partition function that describes the vortex-liquid-to-solid transition, and which is known to have a weak first-order transition at $g_\alpha = g_M \approx -6.7$. This has been established in detailed Monte Carlo simulations [15], as well as in the density-functional theory [16]. To find the transition field with the full τ -dependence of the OP included we assume that the transition is driven by the same mechanism of growing positional correlations between vortices, the only difference now being that the vortices are “straight” in τ -direction over an imaginary time scale $\bar{\tau}$, instead of τ_H .

We identify this time scale with the correlation “length” in τ direction. This ansatz works remarkably well in describing the finite- T first-order transition line in clean YBCO [19], and on that basis we expect it to be a good approximation here as well. The transition field is then determined by the condition

$$g_M = g_\alpha \bar{\tau}^{\frac{1}{2}}, \quad (12)$$

for $\bar{\tau} > 1$ in units of τ_H . To approximately determine $\bar{\tau}$ we will use the self-consistent Hartree approximation [19] to the action in (11). The correlation time is then defined as

$$\bar{\tau} = \frac{g_\tau}{g_\alpha + \langle |\Phi(\mathbf{r})|^2 \rangle / 4}, \quad (13)$$

where the quantum mechanical average appearing in (13) is determined self-consistently as

$$\langle |\Phi(\mathbf{r})|^2 \rangle = \frac{1}{2\pi} \int \frac{d\omega}{g_\tau |\omega| + g_\alpha + \langle |\Phi(\mathbf{r})|^2 \rangle / 4}. \quad (14)$$

Solving Eqs. (12)-(14), one obtains the equation for the first-order transition field

$$H_{sm} = \frac{2\Omega^2}{ev_F^2} e^{-2/g_{\text{eff}}}, \quad (15)$$

where the effective coupling satisfies

$$g_{\text{eff}}^{-1} = g^{-1} + \frac{4a|g_M|\sqrt{\ln \Omega_1}}{\pi} \frac{\sqrt{2eH_{sm}}}{k_F}, \quad (16)$$

in the $\Omega_1 \rightarrow \infty$ limit. The parameter Ω_1 is a dimensionless upper cutoff we introduced to regularize the integral in (14). It may be chosen to yield the correct answer when the next order in “frequency” (*i.e.*, ω^2) term is kept in the effective action, for example. Since Ω_1 appears only under a log the result is little sensitive to its precise value. More importantly, it is evident that g_{eff} is smaller than g which in turn implies that the true transition field H_{sm} is below the mean-field H_0 , which would correspond to the $g_M = 0$ case.

In Fig. 2 we present the H - g phase diagram for the 2D system in the magnetic field and at $T = 0$. The superconductor-metal phase transition induced by the order parameter fluctuations is first-order. The mean-field result represented by the dashed line is included for comparison. Here we have assumed $\Omega = \epsilon_F$, $\Omega_1 = 10^4$, and $g_M = -7.0$. The mean-field and the true transition field are indistinguishably close at very small coupling, but they start to differ significantly at larger couplings. In principle, one may also expect a somewhat renormalized value of g_M from the static value (≈ -7), but the difference does not qualitatively alter our results.




FIG. 2. H - g phase diagram of superconductor-to-metal QPT in 2D in a magnetic field. The dashed line corresponds to the mean-field second-order transition. The solid line is determined by solving Eqs. (15) and (16) and corresponds to the first-order transition induced by the quantum fluctuations of the superconducting order parameter.

IV. EFFECTS OF DISORDER

So far we have completely neglected the effects of static disorder on the superconducting transition. Since the inclusion of disorder complicates the problem significantly, we will discuss its effects only qualitatively. First, it should be possible to model disorder by including a random potential term $V(\mathbf{r})|\Phi(\mathbf{r})|^2$ into the OP effective action in (11). That such a term indeed arises in the OP theory was demonstrated by one of us [9] in a related problem of disordered d -wave superconductor. For simplicity one may assume that the random potential is uncorrelated in space. With this term included one faces an interacting theory with quenched disorder (and in the LLL) which is notoriously difficult to analyze. So in what follows we assume that disorder is strong (compared to the quartic term), so that the self-consistent Hartree treatment of the interaction may be a reasonable starting point [20]. In this spirit we replace the quartic term in (11) as

$$\Phi^4 \rightarrow \langle \Phi^2 \rangle \Phi^2, \quad (17)$$

where the average is self-consistently determined as

$$\langle |\Phi(\mathbf{r})|^2 \rangle = \frac{1}{2\pi} \sum_n \int d\omega \frac{|\phi_n(\mathbf{r})|^2}{g_\tau |\omega| + \varepsilon_n}, \quad (18)$$

where ϕ_n are the LLL eigenfunctions, and ε_n eigenvalues of the random potential, Hartree “screened” by the interactions

$$\tilde{V}(\mathbf{r}) = g_\alpha + V(\mathbf{r}) + \frac{1}{4} \langle |\Phi(\mathbf{r})|^2 \rangle. \quad (19)$$

The superconducting phase transition in this approach would correspond to the vanishing of the lowest eigen-

value ε_n and condensation into the corresponding extended random eigenstate [21]. This transition is expected to be continuous, but to verify this scenario one needs to implement the self-consistent procedure numerically, which we leave for future work. The reader should note however, that the main effect of disorder is to lift the degeneracy of the LLL manifold, and thus restore the possibility of a continuous transition.

In case of weak disorder the above Hartree approximation becomes inadequate and we may only speculate what happens with the transition. Our prejudice, which we discuss more shortly, is that the transition remains first order for weak disorder, and turns continuous only at some critical disorder strength.

V. SUMMARY AND DISCUSSION

Our conclusion of a first order transition in the clean case is in agreement with the renormalization group studies of Brézin, Nelson, and Thiaville [14] and more recently of Moore and Newman [22]. These authors have shown that due to macroscopic degeneracy of the LLL the renormalization group flow in dimensions less than six is always unstable, which is usually interpreted as a sign of a first-order transition. Although they studied a thermal, and not quantum, Abrikosov transition, their methods and conclusions can be readily translated to our case. Furthermore, our conclusion is also in agreement with the large- N treatment of the Abrikosov transition [23–26] at finite temperature. As for the disorder case, Moore and Newman [22] also demonstrated that with weak disorder the renormalization group flow remains unstable, which would indicate that the transition is still discontinuous. The case of strong disorder is outside the domain of validity of their perturbative approach, and we feel that the self-consistent Hartree treatment of the interaction term we discussed is more appropriate.

Our theory offers a natural explanation for the hysteretic behavior observed at the $T = 0$ superconductor-metal transition by Mason and Kapitulnik. We argue that it is a consequence of the fluctuation induced first-order transition. Also, that the non-superconducting state appears metallic, and not insulating, may be related to the fact that a weak magnetic field cuts off the weak-localization effects, and thus relegates the localization effects in 2D to lower temperatures [27]. The observed anomalously small resistivity and the large magnetoresistance of the Mason and Kapitulnik metal could be related to the strong superconducting fluctuations near the critical field. Additional support for this picture comes from the experimental observation that the resistivity away from the critical field H_{sm} vanishes as $R \sim (H - H_0)$, where $H_0 > H_{sm}$ [6]. This power-law follows naturally from our theory as follows. Away from the critical field (outside the critical region dominated by the OP fluctuations) the transition appears continuous, and the resis-

tivity should vanish according to the simple (Aslamazov-Larkin like) scaling [28]

$$R \sim \xi^{d-2}, \quad (20)$$

where ξ is the superconducting correlation length. The GLW action (10) for the OP at the mean-field level implies $d = 0$ (since the OP is confined to the LLL which completely eliminates the gradient terms in 2D). At the mean-field level $\xi \sim 1/(H - H_0)^{1/2}$, so the power counting implies

$$R \sim (H - H_0), \quad (21)$$

in the crossover region, precisely as seen in the experiment [6]. This, of course, ceases to be valid upon entering the critical region, in which, as we argued, fluctuations eventually drive the transition first order at a lower critical field H_{sm} .

Finally, we note that the GLW theory in Eq. (10) has the frequency dependence characteristic of a dissipative system. This is analogous to what was found in the theory of disordered d -wave superconducting phase transition at $T = 0$ [9], and is related to the pair-breaking nature of the magnetic field. This may provide the theoretical basis for the Mason and Kapitulnik interpretation of the superconductor-metal transition [6].

To summarize, we have studied the $T = 0$ superconducting phase transition for a 2D system in a magnetic field. We derived an effective Ginzburg-Landau-Wilson action for the fluctuating superconducting order parameter which enables one to investigate the effects of quantum fluctuations and the order of the phase transition. It is argued that without, or with weak disorder, the quantum superconductor-metal phase transition is of first order. For the case of strong disorder we expect that the possibility of a continuous phase transition is restored.

ACKNOWLEDGMENTS

We are grateful to Prof. S. Sachdev and Dr. D. Lee for useful discussions. This work is supported by NSERC of Canada and NSC of Taiwan (under the grant No. 89-2112-M-003-027). IFH is also supported by an award from Research Corporation.

APPENDIX A: DERIVATION OF S_2

In this Appendix we give the explicit derivation of quadratic S_2 in (6). If we write $S_2 = \int d\omega \bar{S}_2(\omega)$, based on the diagram in Fig. 1, one has at $T = 0$ (apart from the constant term)

$$\bar{S}_2(\omega) = -\frac{V}{2} \times \int \frac{d\nu}{2\pi} d\mathbf{r}_1 d\mathbf{r}_2 G_{\nu+\omega}(\mathbf{r}_1, \mathbf{r}_2) G_{-\nu}(\mathbf{r}_1, \mathbf{r}_2) \Delta_\omega^\dagger(\mathbf{r}_1) \Delta_\omega(\mathbf{r}_2), \quad (A1)$$

where Δ_ω is given by (5) with $C_n(\tau) \rightarrow C_n(\omega)$ in terms of LLL. In the semi-classical approximation, the 2D single-particle Green's function G is given by (4) in which

$$G_\nu^0(\mathbf{r}_1, \mathbf{r}_2) = \int \frac{d\mathbf{p}}{(2\pi)^2} e^{i\mathbf{p} \cdot (\mathbf{r}_1 - \mathbf{r}_2)} \frac{1}{i\nu - \epsilon_{\mathbf{p}}} \quad (\text{A2})$$

where $\epsilon_{\mathbf{p}} = \mathbf{p}^2/2m - \epsilon_F$ and the phase $\phi(\mathbf{r}_1, \mathbf{r}_2) = eH(x_1 + x_2)(y_1 - y_2)/2$. We have assumed that the field $\mathbf{A} = H(0, x, 0)$, which leads to $\mathbf{H} = H\hat{z}$. After substitution of the above into (A1) and carrying out the integrations over y_1 and y_2 , one obtains

$$\bar{S}_2(\omega) = -\frac{V}{2} \sum_{n,m} (2\pi)^2 \int \frac{d\nu}{2\pi} dx_1 dx_2 \frac{d\mathbf{p}}{(2\pi)^2} \frac{d\mathbf{t}}{(2\pi)^2} C_n^*(\omega) \times \frac{C_m(\omega) \delta[t_y + eH(x_1 + x_2) - kn] \delta(kn - km) \times e^{it_x(x_1 - x_2)}}{[i(\nu + \omega) - \epsilon_{\mathbf{p}}][-i\nu - (\epsilon_{\mathbf{p}} - \mathbf{v}_F \cdot \mathbf{t})]} \psi_n(x_1) \psi_m(x_2). \quad (\text{A3})$$

Here we have set $\mathbf{t} \equiv \mathbf{q} + \mathbf{p}$ and $\epsilon_{\mathbf{q}} \simeq \epsilon_{\mathbf{p}} - \mathbf{v}_F \cdot \mathbf{t}$ with $\mathbf{v}_F$ the Fermi velocity.

Using $\int \frac{d\mathbf{p}}{(2\pi)^2} = \mathcal{N} \int d\epsilon \int_0^{2\pi} \frac{d\phi}{2\pi}$ (with $\mathcal{N} = m/2\pi$ as the 2D density of states) and the integral (Ω is the usual ultraviolet cutoff)

$$\int_{-\infty}^{\infty} \frac{d\nu}{2\pi} \int_{-\Omega}^{\Omega} d\epsilon \frac{1}{[i(\nu + \omega) - \epsilon][-i\nu - (\epsilon - \mathbf{v}_F \cdot \mathbf{t})]} = \ln \left[\frac{4\Omega^2}{(\mathbf{v}_F \cdot \mathbf{t})^2 + \omega^2} \right], \quad (\text{A4})$$

one obtains after some calculation

$$\bar{S}_2(\omega) = K_2(\omega) \langle |\Delta_\omega(\mathbf{r})|^2 \rangle, \quad (\text{A5})$$

where $\langle |\Delta_\omega(\mathbf{r})|^2 \rangle$ is defined in (7) and

$$K_2(\omega) = -\frac{g}{4\pi eH} \int d\mathbf{t} e^{-\frac{t^2}{2eH}} \ln \left[\frac{4\Omega^2}{(\mathbf{v}_F \cdot \mathbf{t})^2 + \omega^2} \right]. \quad (\text{A6})$$

Here $g = \mathcal{N}V/2$. Expanding $K_2(\omega) = K_2(0) + A|\omega| + B\omega^2 + \dots$, we found the zero-frequency term

$$K_2(0) = -g \ln(2\Omega\tau_H) \quad (\text{A7})$$

with $\tau_H = \ell/v_F$ and $\ell = 1/\sqrt{2eH}$, and the first-order coefficient

$$A = \left. \frac{\partial K_2(\omega)}{\partial \omega} \right|_{\omega \rightarrow 0} = \sqrt{\pi} g \tau_H. \quad (\text{A8})$$

The combination of (A7) and (A8) gives the result in (6).

APPENDIX B: DERIVATION OF S_4

The quartic action S_4 is expressed diagrammatically in Fig. 1. The similar diagram has been calculated by Maki and Tsuzuki [7] for 3D and finite- T . Here we need S_4

in 2D and at $T = 0$. One can write the quartic term as $S_4 = \int d\omega d\omega_1 d\omega_2 \bar{S}_4(\omega, \omega_1, \omega_2)$, where at zero frequencies ($\omega = \omega_1 = \omega_2 = 0$)

$$\bar{S}_4(0) = \frac{V^2}{4} \int \frac{d\nu}{2\pi} d\mathbf{r}_1 d\mathbf{r}_2 d\mathbf{r}_3 d\mathbf{r}_4 G_\nu(\mathbf{r}_1, \mathbf{r}_2) G_{-\nu}(\mathbf{r}_3, \mathbf{r}_2) \times G_\nu(\mathbf{r}_3, \mathbf{r}_4) G_{-\nu}(\mathbf{r}_1, \mathbf{r}_4) \Delta_0^\dagger(\mathbf{r}_1) \Delta_0(\mathbf{r}_2) \Delta_0^\dagger(\mathbf{r}_3) \Delta_0(\mathbf{r}_4). \quad (\text{B1})$$

In analogy to Appendix A, after a lengthy calculation we find

$$\bar{S}_4(0) = \frac{1}{4} g V v_F^{-2} \frac{2\pi}{k} \sum_{n,m,p,q} C_n^* C_m C_p^* C_q R(n, m, p, q), \quad (\text{B2})$$

where for brevity, $C_n \equiv C_n(0)$, and

$$R(n, m, p, q) = \delta(n - m + p - q) \int_0^{2\pi} \frac{d\theta}{2\pi} \frac{1}{\cos^2 \theta} \times \int dx_1 dx_2 dx_3 dx_4 \frac{\Theta(1, 3; 2, 4)}{|x_1 + x_3 - x_2 - x_4|} \times e^{-i \tan \theta e H T} \psi_n(x_1) \psi_m(x_2) \psi_p(x_3) \psi_q(x_4). \quad (\text{B3})$$

Here θ is the azimuthal angle in 2D,

$$\Theta(1, 3; 2, 4) \equiv 1, \quad \text{if } x_1, x_3 > x_2, x_4 \text{ or } x_1, x_3 < x_2, x_4 \\ 0, \quad \text{otherwise}, \quad (\text{B4})$$

and

$$T = -(x_1 - \frac{kn}{2eH})^2 + (x_2 - \frac{km}{2eH})^2 - (x_3 - \frac{kp}{2eH})^2 \\ + (x_4 - \frac{kq}{2eH})^2 + \left(\frac{k}{2eH} \right)^2 (n^2 - m^2 + p^2 - q^2). \quad (\text{B5})$$

One can further solve

$$\bar{S}_4(0) = \frac{1}{4} g V v_F^{-2} \frac{2\pi}{k} \sqrt{\frac{\pi}{4eH}} \sum_{n,m,p,q} \delta(n - m + p - q) \times e^{-Z} C_n^* C_m C_p^* C_q f, \quad (\text{B6})$$

where

$$Z = \frac{k^2}{4eH} \left[n^2 + m^2 + p^2 + q^2 - \frac{1}{4} (n + m + p + q)^2 \right] \\ = \frac{k^2}{16eH} [(n - m)^2 + (n - p)^2 + (n - q)^2 + \\ (m - p)^2 + (m - q)^2 + (p - q)^2] \quad (\text{B7})$$

and

$$f = \int_0^{2\pi} \frac{d\theta}{2\pi} \frac{1}{\cos^2 \theta} \int_0^\infty t dt \int_0^1 du \int_0^u dv e^{-e H t^2 \Lambda} \cosh(\sqrt{e H t} \Sigma). \quad (\text{B8})$$

Here ($\alpha = \tan \theta$)

$$\Lambda = \frac{1}{2} (1 - i\alpha)(1 - u)^2 + \frac{1}{2} (1 + i\alpha)v^2 + \frac{1}{4} (1 + \alpha^2) \quad (\text{B9})$$

and

$$\Sigma = \frac{k}{2\sqrt{eH}} \times [(1 - i\alpha)(1 - u)(n - p) + (1 + i\alpha)v(m - q)]. \quad (\text{B10})$$

As pointed out by Maki and Tsuzuki, due to the factor of e^{-Z} in (B6), there is a dominance of $n = m = p = q$ when $k^2/4eH \gg 1$ (i.e., in the weak-field limit). In this limit $\Sigma \approx 0$, and thus drops out of f in (B8). As a consequence, f becomes independent of n, m, p, q and Eq. (B6) is simplified to

$$\bar{S}_4(0) = \frac{1}{2\mathcal{N}v_F^2} f \langle |\Delta_0(\mathbf{r})|^4 \rangle, \quad (\text{B11})$$

where $\langle |\Delta_0(\mathbf{r})|^4 \rangle$ is given in (9). To the leading order in field, we found

$$f = f(H) = \frac{4\pi}{eH} [\ln(1 + \sqrt{2})]^2. \quad (\text{B12})$$

It is interesting to note that for 3D and finite- T , the same term will be $f \propto -\ln(T/H)$, and divergent at $T \rightarrow 0$ [7].

- [16] I. F. Herbut and Z. Tešanović, Phys. Rev. Lett. **73**, 484 (1994).
- [17] H. Safar *et al.*, Phys. Rev. Lett. **69**, 824 (1992); *ibid.* **70**, 3800 (1993).
- [18] R. Liang, D. A. Bonn, and W. N. Hardy, Phys. Rev. Lett. **76**, 835 (1996).
- [19] I. F. Herbut and Z. Tešanović, Physica C **255**, 324 (1995).
- [20] See also, I. F. Herbut, in *Fluctuation Phenomena in High Temperature Superconductors*, ed. by M. Ausloos and A. Varlamov (Kluwer, Dordrecht, 1997); Z. Tesanovic and I. F. Herbut, Phys. Rev. B, **50**, 10389 (1994).
- [21] Y. Tu and P. B. Wechman, Phys. Rev. Lett. **73**, 6 (1994).
- [22] M. A. Moore and T. J. Newman, Phys. Rev. Lett. **75**, 533 (1995); T. J. Newman and M. A. Moore, Phys. Rev. B **54**, 6661 (1996).
- [23] I. Affleck and E. Brézin, Nucl. Phys. B **257**, 451 (1985).
- [24] L. Radzihovsky, Phys. Rev. Lett. **74**, 4722 (1995).
- [25] I. F. Herbut and Z. Tešanović, Phys. Rev. Lett. **76**, 4450 (1996).
- [26] A. Lopatin and G. Kotliar, Phys. Rev. B **59**, 3879 (1999).
- [27] P. A. Lee and T. V. Ramakrishnan, Rev. Mod. Phys. **57**, 287 (1985).
- [28] D. Fisher, M. P. A. Fisher, and D. Huse, Phys. Rev. B **43**, 130 (1991).

* On leave from National Taiwan Normal University.

- [1] A. M. Goldman and N. Marković, Phys. Today **51(11)**, 39 (1998) and references therein.
- [2] S. Sachdev, *Quantum Phase Transitions* (Cambridge University Press, Cambridge, 1999).
- [3] I. F. Herbut, Phys. Rev. B **61**, 14723 (2000); *ibid.* **58**, 971 (1998); Phys. Rev. Lett. **81**, 3916 (1998).
- [4] M. P. A. Fisher, Phys. Rev. Lett. **65**, 923 (1990).
- [5] A. Yazdani and A. Kapitulnik, Phys. Rev. Lett. **74**, 3037 (1995).
- [6] N. Mason and A. Kapitulnik, Phys. Rev. Lett. **82**, 5341 (1999); cond-mat/0006138.
- [7] K. Maki and T. Tsuzuki, Phys. Rev. **139**, A868 (1965).
- [8] J. A. Hertz, Phys. Rev. B **14**, 1165 (1976).
- [9] I. F. Herbut, Phys. Rev. Lett. **85**, 1532 (2000).
- [10] L. P. Gorkov, Sov. Phys. JETP, **9**, 1364 (1959).
- [11] A. A. Abrikosov, L. P. Gorkov, and I. E. Dzyaloshinsky, *Methods of Quantum Field Theory in Statistical Physics* (Dover, New York, 1975).
- [12] A. A. Abrikosov, Sov. Phys. JETP **5**, 1174 (1957).
- [13] In general the result could be more complicated. We employ a similar approximation as that used in Ref. [7] appropriate for low fields which leads to a complete independence of the coefficient on LLL (see also Appendix B).
- [14] E. Brézin, D. R. Nelson, and A. Thiaville, Phys. Rev. B **31**, 7124 (1985).
- [15] Z. Tešanović and L. Xing, Phys. Rev. Lett. **67**, 2729 (1991); Y. Kato and N. Nagaosa, Phys. Rev. B **47** (1993); J. Hu and A. H. MacDonald, Phys. Rev. Lett. **71**, 432 (1993); R. Sasik and D. Stroud, Phys. Rev. B **49**, 16074 (1994).